

ADEGLOSS 10



MOISTURE-CURING EXPANDING POLYURETHANE RESIN

Moisture-curing resin that can be used both before and after sanding the parquet for small repairs of strips that are not bonded perfectly to the subfloor.

TECHNICAL CHARACTERISTICS:

- Excellent expansion properties
- Solvent-free
- Excellent adhesive power

WHERE IT CAN BE APPLIED:

- Old wood flooring
- Pre-finished floors
- Unfinished floors

DO NOT USE:

- On exteriors
- To lay flooring

SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Viscous liquid
Colour:	Brown
Brookfield viscosity at 20 °C (mPa*s):	4000 - 5000
Yield:	Depending on use and thickness
Workability time (minutes):	10 - 15
Usage temperature (°C):	+10 - +30
Ready for walking on (hours):	3 - 4
Film hardening (hours):	12 - 24 hours (depending on use and thickness applied)
Application/Equipment:	Special dropper (syringe)
Equipment cleaning:	SOLVENTE GR7 solvent, before the product sets
Storage (months): temperature between +5 °C and +25 °C	6
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	250 ml containers with spout. Boxes of 20.
Usage limitations:	Allow the product to reach 20 °C before applying Frost sensitive Once the product has been opened it will have a natural tendency to harden Always use suitable personal protective equipment

PREPARING THE SURFACE

Drill a small hole in the plank at the point where it is not firmly bonded.

APPLICATION

Allow the product to reach room temperature before use. Apply 2–3 drops of water under the wood pieces to be fitted, possibly at the junction. After 2 minutes, add a small dose of ADEGLOSS 10 in the same place. Be careful not to use too much ADEGLOSS 10, as it swells significantly during the hardening phase. ADEGLOSS 10 is a product that adheres strongly to varnish. For this reason, leakage of the product from cracks, which will result in damage to the surface being treated, must absolutely be avoided. Ambient temperature between 15 and 25 °C, relative humidity no greater than 75%. Always use suitable personal protective equipment. Always consult the technical and safety data sheet for the product.

HAZARD PICTOGRAMS:

