

# LEVELLERS, PRIMERS AND ADDITIVES



# ADEPROMOT CEM DL

# WATER-DISPERSED CONSOLIDATING RESIN

Synthetic resin-based, water-dispersed consolidating fixative for dusty or friable wall surfaces or screeds. For bonding, only use our vinyl or acrylic adhesives.

## **TECHNICAL CHARACTERISTICS:**

- Water-based monocomponent
- Dust-repellent for concrete screeds
- Suitable for laying floors using water-based acrylic and vinyl adhesives
- Adhesion promoter for PAVILAST R ADECEM FIBER

#### WHERE IT CAN BE APPLIED:

- Traditional concrete screeds
- Anhydrite screeds (calcium sulphate)

#### DO NOT USE:

- On non-absorbent bases (glass, marble, tiles, etc.)
- On surfaces subject to continual rising damp that are not protected by a vapour seal barrier

## **SPECIFIC CHARACTERISTICS (normal conditions):**

Appearance:	Thick liquid
Viscosity, Ford 4 at 20 °C (seconds):	11 - 14
Dry (%):	21 - 23
Yield: (g/m²):	150 - 250
Working life (minutes):	5 - 20
Usage temperature (°C):	+15 - +25
Time before use (days):	1 - 3
Film setting (hours):	24 - 48 hours (depending on use and thickness applied)
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Storage (months): maximum temperature +5 °C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	10 kg containers
Recommendations for use:	Do not apply in damp environments Frost sensitive Always use suitable personal protective equipment Always consult the technical and safety information sheets Allow the product to reach 20 °C before applying

### SURFACE PREPARATION:

Always use suitable tools to check the moisture content in the sub-floor. The sub-floor must be compact, free from moisture and with loose parts, such as chalk, dust, oil or wax residue cleaned off.

#### APPLICATION:

Allow the product to reach 20 °C before use. Apply liberally to the sub-floor with a roller or brush. If you need to improve penetration, the product can be diluted at a ratio of 1:1 with clean water. Always check the moisture content of the screed before bonding <2% (<0.5% anhydrite (calcium sulphate)).

Ambient temperature between 15 °C to 25 °C, relative humidity no greater than 75%. Always use suitable personal protective equipment. Always consult the technical and safety data sheet for the product.

#### NOTES

Can be used as an adhesion promoter for applications with PAVILAST R or ADECEM FIBER (see technical data sheet).

# HAZARD PICTOGRAMS:

-- -- --

ADESIV S.R.L. Via delle Rose, 31 - 36061 Bassano del Grappa (VI) - ITALY Tel.: +39(0)424-566 406 - Fax: +39(0)424-566 473 - www.adesiv.it - E-mail: info@adesiv.it

REV. 04 = 2023