



FILLER PLUS

WATER-BASED BINDING RESIN FOR FILLING WOODEN FLOORS

Water-based bonding resin for skimming and grouting wooden floors with cracks. FILLER PLUS is mixed with wood dust produced with extremely fine sanding.

TECHNICAL CHARACTERISTICS:

- Odourless monocomponent
- Water-based
- Good filling power

WHERE IT CAN BE APPLIED:

- 10 mm non-interlocking solid wood flooring
- Mosaic parquet flooring
- (Industrial) solid wood strip flooring
- Tongue-and-groove interlocking solid wood flooring
- Other wood flooring with gaps

DO NOT USE:

- On non-absorbent bases
- On materials other than wood or on already varnished pre-finished floors

SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Thick liquid
Brookfield viscosity at 20°C (mPa*s):	3000 - 5000
Dry (%):	16 - 20
Yield:	15 - 25 m ² /l (depending on the format of the flooring and cracks)
Dry dust free (minutes):	30 - 40
Sandpapering (hours):	1 - 2
Usage temperature (°C):	+15 to +25
Application/Equipment:	Smooth stainless steel plastering trowel
Equipment cleaning:	Water, before the product sets
Storage (months): temperature between +5 °C and +25 °C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	10 L kits (containers of 5 litres each)
Usage limitations:	Do not apply in damp environments. Frost sensitive. Given the large variety of wood types on the market, it is always advisable to carry out a test to check for any variations in colour of the wood being treated. Allow the product to reach room temperature of 20 °C before application. Always use suitable personal protective equipment Always consult the technical and safety information sheets

SURFACE PREPARATION:

Ensure all flooring elements are firmly secured to the surface. Sand the flooring to be treated carefully to obtain a surface free from oil, grease and wax.

APPLICATION:

Allow the product to reach room temperature before use. To obtain an even mix, the product should be mixed in a ratio of approximately 1:1 with the dust created when sanding the surface being treated. Spread the product with a smooth stainless steel plastering trowel, applying the mix to the cracks, or preferably applying a complete skim coat to the flooring. Repeat this step several times if necessary. Once dry (approximately 1 - 2 hours under normal conditions), sand with fine abrasive paper, removing dry product residue completely. Always check that wood moisture is between 8% to 12%, and that the ambient temperature is between 15 °C to 25 °C and relative humidity not above 75%. Always use suitable personal protective equipment. Always consult the technical and safety data sheet for the product.

NOTES:

Failing to remove excess bonding product may lead to variations in shade of the flooring after painting. Given the large variety of wood types on the market, it is always advisable to carry out a test to check for any variations in colour of the wood being treated.

HAZARD PICTOGRAMS:

-- -- --