



LEGASTUCCO L100

BINDING RESIN FOR SMOOTHING WOODEN FLOORS

Quick-drying solvent-based binding resin for mixing with wood powder to grout and smooth parquet floors.



TECHNICAL CHARACTERISTICS:

- Single-component
- Colourless
- High-performance (filling properties)
- Rapid sandpapering
- Can be painted or varnished with water or solvent-based products

SPECIAL PROPERTIES:



Emission class as per French regulations.

WHERE IT CAN BE APPLIED:

- Flooring with non-locking 10-mm solid wood battens
- Mosaic parquet flooring
- Solid wood strip flooring (industrial)
- Interlocking tongue-and-groove flooring

DO NOT USE:

- On non-absorbent bases
- On materials other than wood or finished flooring already varnished



LEGASTUCCO L100



SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Colourless viscous liquid
Viscosity (@ 20 C°; Brookfield)	900 – 1100
Yield	100/120 gr/m ² (may vary depending on the porosity and the cracks of the surface to be treated)
Usage temperature (°C):	+10 to +30
Dry dust free (minutes)	20 - 30
Sandpapering (minutes)	40 - 60
Application/Equipment:	Smooth stainless steel
Equipment cleaning:	SOLVENTE GR7 solvent, before the product sets
Storage (months): temperature of between +5°C and +25°C	12
Disposal information	Dispose of in compliance with the local and national regulations in force
Packs	10 l
Usage limitations:	Make sure the room is ventilated during use and during the hardening stage, avoiding draughts. Inflammable product. Proceed with varnishing using our water or solvent-based single or two-component varnishing products.
GISCODE	RU1

PREPARING THE SURFACE

Polish the parquet floor first to obtain a smooth surface, free of oil, grease and wax.

APPLICATION

Leave the product to reach room temperature and stir it thoroughly before use. Apply at an ambient temperature between 10°C and 30°C. The product should be mixed in a 1:1 ratio to obtain a homogeneous paste with fine dust obtained by sanding the base being treated.

Given the large variety of types of wood present on the market, it is always advisable to carry out tests to verify possible differences in tone. Spread the product with a smooth stainless steel plastering trowel, inserting the paste in the gaps, or preferably by applying a complete layer to the flooring. Repeat this step several times if necessary.

Once dry (approximately 40 - 60 minutes under normal conditions), sand with fine abrasive paper, removing dry product residue completely. Failing to remove excess bonding product may lead to floor colour changes after varnishing.

Remove residual bonding agent from the trowel using our SOLVENT GR7 before the product has set. LEGASTUCCO L 100 can only be removed mechanically once it has hardened. Proceed with varnishing using our water or solvent-based single or two-component varnishing products.

Always use adequate individual protection devices. Always consult the technical and safety information for the product.