



## LEVELING PRIMERS AND ADDITIVES

### PAVILAST K31



#### WATER-DISPERSION CONSOLIDATING RESIN

Synthetic-resin water-dispersion consolidating fixative for powdery or friable wall surfaces or slabs. For gluing only use our vinyl glues or acrylics.

**If necessary, the product can be diluted with a 1:5 ratio with water to assist penetration.**

#### TECHNICAL CHARACTERISTICS:

- Monocomponent
- Concentrated product
- Dustproof for concrete screeds
- Suitable for laying floors using water-based acrylic and vinyl adhesives
- Adhesion promoter for PAVILAST R - ADECEM FIBER

#### SPECIAL PROPERTIES:



Emission class as per French regulations.

#### WHERE IT CAN BE APPLIED:

- Traditional concrete screeds
- Anhydride or chalk screeds
- Preparation of synthetic mortars
- For sealing old flooring that is unstable or coming away in parts

#### DO NOT USE:

- On radiant screeds
- On non-absorbent bases (glass, marble, tiles, etc.)
- In renovation work in presence of individuals sensitive to solvents
- On surfaces subject to continual rising damp that are not protected by a vapour seal barrier
- On screeds containing materials that may dissolve or weaken upon contact with the solvent

## PAVILAST K31



Appearance:	Thick liquid
Viscosity (@20°C; Ford #4):	2000 - 3000
Dry (%):	48 - 50
Yield (g/m <sup>2</sup> ):	300 - 500 (diluted)
Working life (minutes):	5 - 20
Usage temperature (°C):	+15 - +25
Time before use (days):	5 - 7
Film hardening (hours):	24 - 48 hours (depending on use and thickness applied)
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Storage (months): highest temperature +5°C	12
Disposal information	Dispose of in compliance with the local and national regulations in force
Packs	10 kg buckets.
Recommendations for use:	Do not apply in damp environments Frost sensitive Always use personal protective equipment Acclimatise the product at 20°C before applying

### PREPARING THE SURFACE

Always use suitable instruments to check the moisture content in the subfloor. The base must be compact, and free from moisture and loose fragments such as chalk, dust, oil or wax residue.

### APPLICATION

Acclimatise the product at 20°C before use. Dilute 1 kg of product with 7 - 10 litres of clean water (depending on the absorption of the base being treated) and mix to obtain a homogeneous mixture. Apply liberally to the base with a roller or brush. Always check the moisture content of the screed before gluing <2% (<0.5% anhydrite).

Ambient temperature between 15 and 25°C, relative humidity no greater than 75%. Always use adequate individual protection devices. Always consult the technical and safety data sheet for the product.

### NOTE

Can be used as an adhesion promoter for applications with PAVILAST R (see technical data sheet).