



## SMILE

### MATT PAINT FOR VINYL AND LAMINATE FLOORS

Ideal for regenerating LAMINATE, PVC, SPC, and LVT floors. Perfect protection in a single coat, without sanding. No primer required.


#### TECHNICAL CHARACTERISTICS:

- Two-component polyurethane in water dispersion
- Direct application without adhesion promoters
- High resistance to foot traffic and chemical agents
- Covers superficial scratches and revives dulled surfaces
- Coverage  $\approx 15 \text{ m}^2/\text{L}$  per coat
- Odourless, ideal for occupied environments
- Fast application and return to service within the same day

#### WHERE IT CAN BE APPLIED:

- On LVT flooring
- On SPC flooring
- On PVC flooring
- On LAMINATE flooring

#### SPECIAL PROPERTIES:

	Emission class as per French regulations.
--	---

#### SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Milky liquid
Viscosity, Ford 4 at 20 °C (seconds): Catalysed product	40 - 45
Gloss value at 60 degrees	Matte: 4 - 6
Mixing ratio:	10: 1
Yield: (g/m <sup>2</sup> ):	50 - 70 (the yield of the product may vary depending on the porosity or flatness of the surface being treated)
Dry dust free (minutes):	45 - 60
Sanding (hours):	3 - 6
Final setting (days):	5 - 7
Walkability (hours):	18 - 24
Usage temperature (°C):	+ 15 - +25
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Product removal:	Water, before the product sets
Storage (months): temperature between +5 °C and +25 °C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	Packaging: comp. A 2.5 L + comp. B 0.25 L
Note:	Stir well before use
Usage limitations:	Do not apply in damp environments, protect from frost, avoid drafts, and condition the product before application. Always use appropriate personal protective equipment. Always consult the Technical Data Sheet and the Safety Data Sheet.

CONTINUE



## SMILE

**SURFACE PREPARATION:** The surface to be treated must be thoroughly cleaned and degreased using alcohol. Before application, carefully vacuum the floor, removing any excess dirt and dust. The substrate must be dry, with an ambient temperature between 12 and 25 °C and relative humidity not exceeding 75%.

**APPLICATION:** Condition and thoroughly shake the product before use. Slowly add the hardener (component B) to component A under continuous stirring and mix carefully. Wait approximately 10–15 minutes after mixing the two components before application. Filter the product before use and apply evenly and generously using a roller or brush. If a second coat is required, it must be applied within 48 hours of the first coat to ensure perfect adhesion.

**NOTES:** Wait at least 7 days before carrying out any cleaning or maintenance operations, allowing SMILE to fully cure and reach its maximum performance.

For routine maintenance, we recommend always using our neutral detergent VINYL LAMINA-CLEAN.

Always consult the product Technical Data Sheet.

### HAZARD PICTOGRAMS:

#### Component A

-- -- --

#### Component B

