



UNI PRIMER

MONOCOMPONENT PRIMER

Quick-drying monocomponent primer - anti-yellowing - for parquet. We recommend the use of UNI PRIMER for all quick finishing cycles where you want to limit colour changes to the floor.

TECHNICAL CHARACTERISTICS:

- Single-component
- Rapid drying
- Non-yellowing
- Ideal for rapid varnishing cycles
- Water-repellent action
- Alcohol-based

WHERE IT CAN BE APPLIED:

- Wood flooring
- Surfaces treated with grey or white WB OIL

Appearance:	Colourless liquid
Viscosity (@20°C; Ford #4):	20
Yield (g/m ²):	80 – 100 (the yield of the product may vary depending on the porosity or the flatness of the surface to be treated)
Dry dust free (minutes):	20 - 30
Final hardening, sandpapering (minutes):	60 - 90
Usage temperature (°C):	+ 15 - +25
Application/Equipment:	Roller, brush
Equipment cleaning:	GR7, before the product sets
Product removal:	GR7, before the product sets
Storage (months): temperature of between +5°C and +25°C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	5-litre containers
Note:	(1) Dir. 2004/42/CE cat h bs, max. limit COV 750 g/l The values refer to 20°C and 65% RH.
Usage limitations:	Do not apply in damp environments Frost sensitive Avoid draughts Leave the product to reach room temperature before applying

CYCLE WITH UNI PRIMER + ICE VARNISH PREPARING THE SURFACE

The wood floor must be perfectly smooth, filled and sanded, free of substances that may interfere with adhesion (e.g. oil, wax, silicone). The base being treated must be dry with a moisture content of 8 – 12%. Ambient temperature between 15 and 25°C, relative humidity no greater than 75%. Before applying, it is advisable to sandpaper the surface using paper with grit size 180, then vacuum and clean with an anti-static cloth.

APPLICATION

Leave the product to reach room temperature and stir it thoroughly before use. Apply evenly using a roller or brush. After approximately 1-2 hours in normal conditions, sandpaper with fine grit size 220 paper and apply a coat of ICE varnish. After 8-12 hours, sand and clean the surface and apply a second coat of ICE varnish. Always wear protective gloves. Always consult the technical and safety data sheet for the product.

CYCLE WITH WHITE or GREY COLOURED OIL + UNI PRIMER + ICE VARNISH

Apply white or grey WB OIL in accordance with the instructions in the technical data sheet. Once the oil is dry, apply a coat of UNI PRIMER without sandpapering. After approximately 1-2 hours, rub lightly with abrasive felt to remove any pitting, vacuum the surface and clean with an anti-static cloth, then apply a coat of ICE varnish.