



ICE SPORT FIRE

instructions

FLAME-RETARDANT, ANTI-SLIP, WATER-BASED TWO-COMPONENT VARNISH FOR WOODEN FLOORS

PREPARING THE BASE The wood flooring must be smoothed, filled and sanded thoroughly, and free from loose fragments such as oil, wax and silicone. The surface to be finished must be dry, with 8-12% moisture content. Ambient temperature between 15 and 25°C, relative humidity no greater than 75%. After sanding with 150/180 grit, vacuum the whole surface and then clean with an anti-static cloth.

APPLICATION Bring up to room temperature and shake carefully before use. Add the hardener (component B) to component A, while stirring, and mix carefully. After mixing the two components, wait approximately 10–15 minutes before applying. Filter the product before use and apply an even coat using a roller or brush, with a quantity of at least 120 gr/m² total to obtain the flame-retardant class, or 180 gr/m² to obtain the flame-retardant and anti-slip class.

If it is difficult to apply the necessary amount in a single coat, apply a second coat. Always wear protective gloves. Always consult the technical and safety data sheet for the product.

MAINTENANCE: For optimal maintenance of flooring varnished with ICE SPORT FIRE, we recommend regular use of our neutral detergent PARQUETPRO (see technical data sheet).

Always consult the product data sheet to ensure compatibility of the painting cycles.